

Collection **Synergy bouclés** pdt type: **multi-purpose** (v.1.5)
 Design name **Sabik** 12 colourways

01-dune	07-stone	13-indigo	19-linden
03-flax	09-rhodium	15-hydro	21-antique
05-pebble	11-anthracite	17-mineral	23-peony

width	143cm or 56 ¼"	composition	96% GRS recycled polyester Inherent FR 4% polyester Inherent FR
weight	426g/m ²		
sound absorption	ISO 11654 see FR-One.com	v. repeat	plain
		h. repeat	plain






our standards

			
---	---	---	---

applications



cleaning instructions

			recommended at 60°C or 140°F gentle cycle, do not bleach, do not tumble dry, low temperature iron, gentle dry clean dimensional change 40°C -0.53 to -0.66% after ironing 60°C -1.73 to -2.86% American Hospital washing standard test report AATCC96 download available on FR-One.com
			

Marindale	50,000	rub fastness dry/wet	4-5/4-5
Wysenbeek	100,000	seam slippage warp/wef	2/2
pilling/brush pill	4-5/4-5	tearing strength warp/weft	215N / 80N
colour fastness to wear/light/water	4/6/5	tensile strength warp/weft	1100N/5cm / 880N/5cm
		dimensional stability	stable

American FR tests	NFPA 701 #1- 2010 & NFPA 260A/UFAC Class 1 & ASTM E84	
British FR tests	BS5867 & BS7176 2007 Medium Hazard inc. BS EN 1021-1 & 2 2006* BS 5852 : 2006** (source 5 or Crib5)	
Canadian FR tests	CAN/ULC S109	* upholstery use only
European FR tests	EN 13773 & EN 1021* part 1 & part 2	** in conjunction with a
French FR tests	NF P 92 503-507 (M1)	modified combustion
German FR tests	DIN 4102 (B1)	foam CMHR equal or
IMO FR tests	FTPC part 7 (A471) part 8* (A652) & part 9	superior to 35kg/m3

product type / country of origin	yarn dyed jacquard / 5407530000 Turkey
average piece size	35mtr face in
qty special colour	300mtr minimum dye batch & 100mtr incremental

Collection Synergy bouclés pdt type: multi-purpose (v.1.4)
 Design name Saiph 12 colourways

02-sand	08-dice	14-denim	20-tea
04-linen	10-metal	16-reef	22-ocre
06-concrete	12-slate	18-lichen	24-nostalgia

width	143cm or 56 ¼"	composition	95% GRS recycled polyester Inherent FR 5% polyester Inherent FR
weight	420g/m ²	v. repeat	2cm or ¾"
sound absorption	ISO 11654 see FR-One.com	h. repeat	5.5cm or 2"

our standards



Global Recycled Standard
Certified by Control Union
CU1036513



Environmental Association
ISO 14001:2015



OEKO
TEX®

STANDARD
100
2111231
Centexbel



0493/23






applications







cleaning instructions

recommended at 60°C or 140°F gentle cycle, do not bleach, do not tumble dry, low temperature iron, gentle dry clean

dimensional change 40°C -0.53 to -0.60%
after ironing 60°C -1.73 to -2.86%

American Hospital washing standard test report AATCC96 download available on FR-One.com

Marindale	50,000	rub fastness dry/wet	4-5/4-5
Wysenbeek	100,000	seam slippage warp/weft	2/3
pilling/brush pill	4/4-5	tearing strength warp/weft	158N / 81N
colour fastness to wear/light/ water	4/4/4-5	tensile strength warp/weft	1100N/5cm / 740N/5cm
		dimensional stability	stable

American FR tests	NFPA 701 #1- 2010 & NFPA 260A/UFAC Class 1 & ASTM E84	
British FR tests	BS5867 & BS7176 2007 Medium Hazard inc. BS EN 1021-1 & 2 2006* BS 5852 : 2006** (source 5 or Crib5)	
Canadian FR tests	CAN/ULC S109	* upholstery use only
European FR tests	EN 13773 & EN 1021* part 1 & part 2	** in conjunction with a
French FR tests	NF P 92 503-507 (M1)	modified combustion
German FR tests	DIN 4102 (B1)	foam CMHR equal or
IMO FR tests	FTPC part 7 (A471) part 8* (A652) & part 9	superior to 35kg/m3

product type | country of origin yarn dyed jacquard | 5407530000 / Turkey
 average piece size 40mtr face in
 qty special colour 300mtr minimum dye batch & 100mtr incremental